

ALUMINIUM ALCLAD SHEET

TYPICAL APPLICATIONS

Aerospace Components
Defence Components
High Technology Applications

PRODUCT DESCRIPTION

A high strength 5.1 to 6.1% Zinc alloy solution heat treated and artificially aged to achieve the T6 condition. Also generally available in the 'O' condition for more severe, bending and forming operations.

AECMA Euronorm - BS EN 2092 (T6)

STOCK RANGE

0.008" to 0.249" Thick
(0.203 to 6.32mm)

CUT TO SIZE GUILLOTINED BLANKS

Edge deviation over cut length/width +/- 0.2mm per m (maximum thickness 6.35mm)

FORMABILITY

Fair for 'O' condition.

CORROSION RESISTANCE

Resistance to Atmospheric Attack

Very Good

SURFACE TREATMENT

Anodising

Protective - Excellent
Bright - Very Good
Hard - Excellent
Colour - Very Good

Plating

Special pre-treatment necessary to achieve successful results

Vitreous Enamelling

As Plating.

WELDABILITY

Please contact our Technical Department.

PRODUCTION TOLERANCES

Manufacturing limits are as stated in Table 7.7b to 7.18 in U.S. Aluminium Standards and Data. For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others
Min	REM			1.2		2.10	0.18	5.10		0.05 Each (Max)
Max	REM	0.40	0.50	2.0	0.30	2.90	0.28	6.10	0.20	0.15 Total

MECHANICAL PROPERTIES (MINIMA)

Size Range (in)	Tensile Strength (ksi)	0.2% Proof Stress (ksi)	Elongation on 5.65 √ S ₀ (%)	Elongation on 50mm (%)
0.008 – 0.011	68	58	5	-
0.012 – 0.039	71	61	8	-
0.040 – 0.062	72	62	9	-
0.063 – 0.125	74	64	9	-
0.126 – 0.187	74	64	9	-
0.188 – 0.249	76	65	9	-

NB: Figures shown above are for 'T6' condition.

TECHNICAL SALES ASSISTANCE

Our resident team of qualified metallurgists and engineers will be pleased to assist further on any technical topic.

Biggleswade
01767 604704

Birmingham
01889 576117

Bristol
0117 971 2800

Chelmsford
01245 466664

Ferndown
01202 893755

Gateshead
0191 469 5428

Horsham
01403 261981

Leeds
0113 307 5167

London
020 7241 2430

Nottingham
0115 925 4801

Norwich
01603 789878

www.smithmetal.com
sales@smithmetal.com