

ALUMINIUM PLATE

TYPICAL APPLICATIONS

Aerospace & Defence Components
High Technology Applications

PRODUCT DESCRIPTION

A strong 3.9 to 5.0% Copper alloy, rolled plate specification. Solution treated, artificially aged and stress relieved (control stretched) to achieve the T651 condition.

General Engineering Equivalent - 2014AT651
General Engineering Euronorm - EN 485/515/573
Old BS Spec - HP15TF (BS1470)
AECMA Euronorm - None

STOCK RANGE

1/4" to 4" Thick (6.35 to 101.6mm)

CUT TO SIZE SAWN BLANKS

Cut to length in house to tolerances - Nil + 1.6mm

MACHINABILITY

Good.

CORROSION RESISTANCE

Resistance to Atmospheric Attack
Poor.

SURFACE TREATMENT

Anodising

Protective - Fair
Bright - Unsuitable
Hard - Good
Colour - Fair (Dark Colour Only)

Plating

Very Good

Vitreous Enamelling

Unsuitable

WELDABILITY

Brazing & Soldering - Not Recommended
Oxygen - Not Recommended
Inert Gas - Not Recommended
Resistance, Spot, Beam - Excellent

PRODUCTION TOLERANCES

Manufacturing limits are as stated in the Section 14 of BS 4L100 – Tables (F1, 2, 5, 7 & 8). For further assistance please contact our Sales Dept / Laboratory.

CHEMICAL COMPOSITION (WEIGHT %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti + Zr	Pb	Sn
Min	Rem	0.50		3.9	0.40	0.20						
Max	Rem	0.90	0.50	5.0	1.2	0.80	0.10	0.20	0.20	0.2	0.05	0.05

MECHANICAL PROPERTIES (MINIMA FOR T651 CONDITION)

Direction of Test Sample	Thickness Range (mm)		0.2% Proof Stress (MPa)	Tensile Strength (MPa)	Elongation On 50mm (%)	Elongation On $5.65\sqrt{S_0}$ (%)
	Over	Up to & Including				
Long Transverse	6	12.5	410	460	7	-
	12.5	25	410	460	-	6
	25	40	400	450	-	5
	40	63	390	430	-	5
	63	90	390	430	-	4
	90	115	370	420	-	4
	115	140	350	410	-	4
Short Transverse	25	90	360	420	-	2.5
	90	115	340	410	-	2.5
	115	140	340	400	-	2.5
Longitudinal	25	40	410	450	-	6
	40	90	400	430	-	6
	90	115	380	430	-	6
	115	140	360	420	-	6

Biggleswade
01767 604704

Birmingham
01889 576117

Bristol
0117 971 2800

Chelmsford
01245 466664

Ferndown
01202 893755

Gateshead
0191 469 5428

Horsham
01403 261981

Leeds
0113 307 5167

London
020 7241 2430

Nottingham
0115 925 4801

Norwich
01603 789878

www.smithmetal.com
sales@smithmetal.com

All information in this data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres Ltd 2007