

2011 Aluminium

Technical Datasheet



Free Machining Aluminium Alloy

Service. Quality. Value.

Applications

- Machine parts
- Automotive components
- Weaponry & munitions
- Fasteners / Fittings

Key features:

- Excellent machinability
- Can be used to produce highly complex, detailed parts
- Material suitable for automatic lathes
- Poor corrosion resistance

Product Description

Alloy 2011 is known as a free machining alloy or 'FMA' - this means that the material has excellent machinability and is suitable for use on automatic lathes. The alloy displays poor corrosion resistance and therefore anodising will be required for additional surface protection. Whilst weldability is also very poor, 2011 aluminium is a highly versatile aluminium. With excellent machinability the material can be used to produce highly complex and detailed parts.

Related Material Specifications

- AlCu6BiPb
- A92011
- 3.1655
- FC1
- CB60
- AlCuBiPb

Corrosion Resistance

Poor

Weldability

Extremely poor. As 2011 aluminium is used predominantly in machined parts, welding is seldom necessary.

Availability

Bar

Chemical Composition (weight %)

Weight (%)	Si	Fe	Cu	Pb	Bi	Zn	Al	Other
min.			5.0	0.2	0.2	0.3	Bal	
max.	0.4	0.7	6.0	0.6	0.6	0.3	Bal	0.15

Physical Properties

Melting Point	535°C
Density	2.82 Kg/m ³
Thermal conductivity	138 W/m.K
Thermal expansion coefficient	23 x 10 ⁻⁶
Modulus of elasticity	71 GPa

Mechanical Properties

Temper	Proof Stress (MPa)	Tensile Strength (MPa)	Shear Strength (MPa)	Elongation A5 (%)	Elongation A50 (%)	Hardness Brinell HB	Hardness Vickers HB	Fatigue Endur. Limit (MPa)
T3	290	365	220	15	15	95	100	250
T4	270	350	210	18	18	90	95	250
T6	300	395	235	12	12	110	115	250
T8	315	420	250	13	12	115	120	250

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

