

3103 Aluminium

Technical Datasheet



Service. Quality. Value.

Commercial Aluminium Alloy

Applications

- Heat exchangers
- Heating & cooling systems
- Aircraft & military components
- Vehicle radiators
- Corrugated roofing
- Cooking utensils & kitchen equipment
- Air conditioning evaporators

Product Description

3103 aluminium alloy is a commercial aluminium which is close in properties to 3003. With very good resistance to atmospheric corrosion and excellent mechanical properties, 3103 is a versatile alloy which is used in the aerospace, oil and gas industry and automotive sector amongst others. The material has improved mechanical properties over 1000 series aluminium alloys, especially at elevated working temperatures. This feature widens the use of the alloy as a construction cladding material.

Key features:

- Medium strength alloy
- Good resistance to atmospheric corrosion
- Properties very close to 3003
- Very good weldability

Related Material Specifications

- AlMn1

Weldability

Very good

Corrosion Resistance

Very good

Availability

Plate, Sheet

Chemical Composition (weight %)

Weight (%)	Mn	Fe	Cu	Mg	Si	Zn	Cr	Ti+Zr	Al	Other
min	0.90								Bal	0.05
max.	1.50	0.70	0.10	0.05	0.50	0.20	0.10	0.10	Bal	0.15

Mechanical Properties

Tensile Strength	140 MPa min
Elongation A50 mm	8% min
Shear Strength	90 MPa
Hardness Vickers	46 HV
Proof Stress	110 Mpa min

Physical Properties

Density	2.73 g/cm ³
Melting Point	655°C
Thermal Expansion	23.1 x10 ⁻⁶ /K
Modulus of Elasticity	69.5 GPa
Thermal Conductivity	160 W/m.K
Electricity Resistivity	42% IACS

The properties above are for material in the H14 condition

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

