

6063 Aluminium

Technical Datasheet



Service. Quality. Value.

Commercial Aluminium Alloy

Applications

- Architectural
- Extrusions
- Doors
- Window frames
- Shop fittings
- Balustrading

Product Description

6063 aluminium alloy is often referred to as an architectural alloy and is used in the production of intricate extrusions. With an aesthetically pleasing finish and high corrosion resistance the alloy is readily suited to welding and can be easily anodised. 6063 aluminium is most commonly supplied as T6 temper. If supplied in the T4 condition the alloy has good formability.

Key features:

- Medium strength alloy
- Used in intricate extrusions
- Aesthetically pleasing finish
- High corrosion resistance
- T6 temper most common, T4 has good formability

Corrosion Resistance

High

Availability

Extrusions, tube

Chemical Composition (weight %)

	Mn	Fe	Mg	Si	Zn	Ti	Cr	Cu	Al			
min.			0.45	0.20					Bal			
max.	0.10	0.35	0.90	0.60	0.10	0.10	0.10	0.10	Bal			

Mechanical Properties

Tensile Strength	100 MPa
Proof Stress	50 MPa
Shear Strength	70 MPa
Elongation A50 mm	27%
Brinell Vickers	25 HV

Physical Properties

Density	2.70 g/cm ³
Melting Point	600 °C
Thermal Expansion	23.5 x10 ⁻⁶ /K
Modulus of Elasticity	69.5 GPa
Thermal Conductivity	200 W/m.K

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

UK Service Centres

Quality Testing

Smiths Belfast	02895 908 897	Smiths Leeds	0113 307 5167
Smiths Biggleswade	01767 604 704	Smiths London	020 7241 2430
Smiths Birmingham	0121 728 4940	Smiths Manchester	0161 794 8650
Smiths Bristol	0117 971 2800	Smiths Norwich	01603 789 878
Smiths Chelmsford	01245 466 664	Smiths Nottingham	0115 925 4801
Smiths Gateshead	0191 469 5428	Smiths Redruth	01209 315 512
Smiths Horsham	01403 261 981	Smiths Verwood	01202 824 347

0845 527 3331

www.smithmetal.com

info smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.