

7075 Aluminium

Technical Datasheet



Service. Quality. Value.

Commercial Aluminium Alloy

Applications

- Aircraft structures
- Gears & shafts
- Automotive

Product Description

7075 aluminium alloy is a very high strength aerospace aluminium and is commonly used in applications where the strength of the material is critical and where the need for good corrosion resistance is not important. Offering superior stress corrosion resistance, 7075 provides very high yield and tensile strengths which is dictated by the particular chosen temper.

Key features:

- Very high strength aerospace aluminium
- Used where high strength is critical and where good corrosion resistance is not important
- Up to 465 MPa yield strength and 540 MPa tensile strength depending on temper
- Superior stress corrosion

Machinability

Fair

Availability

Bar, sheet, plate

Chemical Composition (weight %)

	Si	Fe	Cu	Mn	Cr	Mg	Zn	Ti	Al	Others
min.			1.20		0.18	2.10	5.10		Bal	
max.	0.40	0.50	2.00	0.30	0.28	2.90	6.10	0.20	Bal	0.15

Mechanical Properties

Tensile Strength 40-78 ksi, 275 - 540 MPa
Yield Strength 24-68 ksi, 455 - 465 MPa

Physical Properties

Density 2.81 g/cm³
Melting Point 635 °C
Modulus of Elasticity 72 GPa
Thermal Conductivity 134-160 W/m.K
Electrical Resistivity 40% IACS

Properties dependent on chosen temper.

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604 604	Birmingham 01889 576 117	Bristol 0117 971 2800	Chelmsford 01245 466 664	Gateshead 0191 469 5428	Horsham 01403 261 981	Leeds 0113 307 5167
London 020 7241 2430	Manchester 0161 794 8650	Nottingham 0115 925 4801	Norwich 01603 789 878	Redruth 01209 315 512	Verwood 01202 824 347	General 0845 527 3331

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2017

