

Aluminium Plate

Typical Applications

- Aerospace Components
- Defence Components
- High Technology Applications

Product Description

A medium strength rolled plate, solution heat-treated, artificially aged and stress relieved arriving at the 'T651' condition. Officially, the scope of the specification covers only thicknesses between 6 and 25mm. Of these, only 12 to 25mm thick are ultrasonically tested. However, ultrasonically tested metal up to at least 127mm thick is commonly made to chemical composition only, although mechanical properties are usually achieved as well.

General Engineering Equivalent - 6082T651
 BS EN Euronorm - EN 573 / 754
 Old BS - HP30TF (BS1470)
 Controlled Stretched
 AECMA Euronorm - BE EN 4202

Production Tolerances

For further assistance please contact our Sales Dept / Laboratory.

Surface Treatment

Anodising

Protective - Good
 Bright - Fair
 Hard - Good / Very Good
 Colour - Good

Plating & Vitreous Enamelling

Special pre-treatment necessary to achieve successful results

Weldability

Brazing & Soldering - Good
 Oxygen - Fair
 Inert Gas - Very Good
 Resistance, Spot, Beam - Very Good

Machinability

Very Good

Corrosion Resistance

Resistance to Atmospheric Attack - Good

Cut Size to Size Sawn Blanks

Cut To Length and Width + / - 1.6mm

Chemical Composition (weight %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Pb	Sn
Min.	Rem	0.7			0.4	0.5						
Max.	Rem	1.3	0.5	0.1	1.0	1.2	0.25	0.1	0.2	0.2	0.05	0.05

Mechanical Properties (Minima)

Size Range (mm)	Tensile Strength (MPa)	0.2% Proof Stress (MPa)	Elongation on 5.65√S ⁰ (%)	Elongation on 50mm (%)
Up to 25mm	295	240	8	8

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

