

L95 Aluminium T651

Technical Datasheet



Service. Quality. Value.

Aluminium Plate

Typical Applications

- High stressed components for commercial & military aircraft
- Rolling stock for machine parts and tools (for rubber and plastics)
- Fixings including screws, nuts, bolts & rivets
- Nuclear applications

Product Description

L95 aluminium alloy is a very high strength plate product which is supplied to the aerospace sector in both commercial and military markets. Normally supplied as T651 temper, the alloy also benefits from a very high fatigue strength. The material may be clad with 7072 which will provide better protection against stress corrosion cracking (SCC).

Availability

Plate

Key features:

- Very high strength alloy
- Very high fatigue strength
- Corrosion protection recommended
- Most common temper for L95 is T651

Related material specifications:

Aluminium alloy L95 - 7075 is covered by standard BS 2L95 (1971). BS2L95 (1971) was superseded by BS EN 2126 on 15 October 1996.

Corrosion Resistance

Corrosion protection recommended for outdoor atmosphere.

Machinability

Fair

Chemical Composition (weight %)

	Zn	Mg	Cu	Fe	Si	Cr	Mn	Ti+Zr	Ni	Sn	Pb	Al	Other
Min.	5.10	2.10	1.20			0.10						Bal	
Max.	6.40	2.90	2.00	0.50	0.40	0.25	0.30	0.20	0.05	0.05	0.05	Bal	0.15

Mechanical Properties

Thickness (mm)	Proof Strength (min)	Tensile Strength (min)	Elongation % (min)
Over 6 to & incl. 12.5	450	530	8
Over 12.5 up to & incl. 25	450	530	6
Over 25 up to & incl. 40	450	530	5
Over 40 up to & incl. 63	440	510	5
Over 63 up to & incl. 90	410	500	5

Properties based on T651 temper and given in the long transverse direction only.


Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

UK Service Centres:

Smiths Belfast	02895 908 897	Smiths Leeds	0113 307 5167
Smiths Biggleswade	01767 604 704	Smiths London	020 7241 2430
Smiths Birmingham	0121 728 4940	Smiths Manchester	0161 794 8650
Smiths Bristol	0117 971 2800	Smiths Norwich	01603 789 878
Smiths Chelmsford	01245 466 664	Smiths Nottingham	0115 925 4801
Smiths Gateshead	0191 469 5428	Smiths Redruth	01209 315 512
Smiths Horsham	01403 261 981	Smiths Verwood	01202 824 347

Quality & Testing:



0845 527 3331

www.smithmetal.com



info@smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading.