

### Hydraulically Tested Aluminium Tube

#### Applications

- Shipbuilding
- Motorboats
- Aircraft structures
- Truck bodies
- Pylons & towers
- Rail coaches

#### Key features:

- Medium to high strength heat-treatable alloy
- Medium fatigue strength
- Very good corrosion resistance
- Typically used in heavy duty structures

#### Product Description

L118 is based on the aluminium material designation 6061. L118 aluminium tube is the least expensive and most versatile of the heat-treatable alloys. It is a medium to high strength heat-treatable material with very good corrosion resistance and medium fatigue strength. L118 is a tube product supplied in the T6 annealed condition, hydraulically tested, offering excellent weldability and formability and is readily disposed to furnace brazing. The alloy is typically used in heavy duty structures.

#### Corrosion Resistance

Very good

#### Availability

Pipe, Tube

#### Chemical Composition (weight %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Other
min.	Rem	0.4		0.15		0.8	0.04				0.05
max.	Rem	0.8	0.7	0.40	0.15	1.2	0.35		0.25	0.15	0.15

#### Mechanical Properties

	0.2% Proof Stress (min)	Tensile Strength (min)	Full Tube Section (min, %)	Strip Test Piece (min, %)
Up to 1mm	240 N/mm <sup>2</sup>	290 N/mm <sup>2</sup>	10	9
1.0mm to 5.0mm	240 N/mm <sup>2</sup>	290 N/mm <sup>2</sup>	12	10
5.0mm to 10.0mm	240 N/mm <sup>2</sup>	290 N/mm <sup>2</sup>	14	12

#### Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

[www.smithmetal.com](http://www.smithmetal.com)

[sales@smithmetal.com](mailto:sales@smithmetal.com)

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

