

Aluminium Alclad Sheet

Typical Applications

- Aerospace Components
- Defence Components
- High Technology Applications

Product Description

A high strength 5.1 to 6.1% Zinc alloy solution heat treated and artificially aged to achieve the T6 condition. Also generally available in the 'O' condition for more severe, bending and forming operations.

AECMA Euronorm - BS EN 2092 (T6)

Production Tolerances

Manufacturing limits are as stated in AMS QQA 250. For further assistance please contact our Sales Dept / Laboratory.

Cut Size to Guillotined Blanks

Edge deviation over cut length/width +/- 0.2mm per m (maximum thickness 6.35mm)

Surface Treatment

Anodising

Protective - Excellent
Bright - Very Good
Hard - Excellent
Colour - Very Good

Plating & Vitreous Enamelling

Special pre-treatment necessary to achieve successful results

Weldability

Please contact our Technical Department

Formability

Fair for 'O' condition.

Corrosion Resistance

Resistance to Atmospheric Attack - Very Good

Chemical Composition (weight %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Others
Min.	REM			1.2		2.1	0.18	5.10		0.05 each (max)
Max.	REM	0.40	0.50	2.0	0.30	2.9	0.28	6.10	0.20	0.15 total

Mechanical Properties (minima, ALCLAD, T6 condition)

Size Range (in)	Tensile Strength (ksi)	0.2% Proof Stress (ksi)	Elongation on 5.65√S ⁰ (%)
0.008 – 0.011	68	58	5
0.012 – 0.039	71	61	8
0.040 – 0.062	72	62	9
0.063 – 0.125	74	64	9
0.126 – 0.187	74	64	9

NB: Figures shown above are for 'T6' condition.

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

