

Drawn Aluminium Tubing

Typical Applications

- Aircraft applications
- Pylons & Towers
- Shipbuilding

Product Description

AMS-WWT-700/6 drawn aluminium tubing is used in applications where medium strength and good corrosion resistance is required. The alloy offers good general machinability and formability. The material also has an aesthetically pleasing appearance after anodizing.

Corrosion Resistance

Good

Key Features

- Good corrosion resistance and formability
- Excellent aesthetic appearance after anodising
- Medium strength
- Good general machining characteristics
- Preferred alloy when welding or brazing is required

Availability

Pipe, tube

Machinability

Good

Chemical Composition (weight %)

	Al	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Other	Total
min.	Bal	0.4		0.15		0.8	0.04				
max.	Bal	0.8	0.7	0.40	0.15	1.2	0.35	0.25	0.15	0.05	0.15

Mechanical Properties (typical)

	Ultimate		Yield		Elongation %	Brinell
	KSI	MPA	KSI	MPA		
O	18	124	8	55	58	30
T4	35	241	21	145	22	65
T6	45	310	40	276	12	95

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

