

Lightweight Engineering Plastic

Typical Applications

- Medical devices
- Manifolds
- Pumps & valves
- Electrical components
- Fluid handling applications
- Housings

Product Description

Noryl PPO (modified polyphenylene oxide) is manufactured from Noryl® resin. A combination of low moisture absorption and low thermal expansion make the material one of the most dimensionally stable thermoplastics available today.

Noryl PPO is used widely in products such as structural components and electrical housings due to the materials excellent insulating characteristics over a wide range of temperatures in service. The thermoplastic is also used in fluid handling applications as it has low moisture absorption.

Key features

- High dielectric strength
- Low moisture absorption
- Excellent impact strength
- Thermal stability
- Long term dimensional stability
- Continuous use in temperature above 220 °F
- Hydrolytic stability
- Good impact resistance

Availability

Rods, plates and tubes

Usability

Noryl PPO is easy to fabricate, paint, and glue

Mechanical Properties

	Units	ASTM Test	EN-265	30% GF
Flexural Modulus	psi	D790	370,000	1,130,000
Flexural Strength @yield	psi	D790	14,400	25,000
Hardness-Rockwell	—	D785	R119	L108
Izod Impact Strength				
Notched @-40°F	ft•lbs/in	D256	2.5	1.8
Notched @73°F	ft•lbs/in	D256	3.5	2.2
Tensile Elongation @break	%	D638	25.0	5.0
Tensile Strength @yield	psi	D638	9,200	17,500

Thermal Properties

	in/in/°F	D696	3.3x10 ⁻⁵	1.4x10 ⁻⁵
Coefficient of Thermal Expansion				
Flammability Rating-UL94				
@.058"	—	—	V-1	V-1
@.240"	—	—	V-0	V-0
Heat Deflection Temperature				
@66psi	°F	D648	—	285
@264psi	°F	D648	254	275


Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

UK Service Centres:

Smiths Belfast	02895 908 897	Smiths Leeds	0113 307 5167
Smiths Biggleswade	01767 604 704	Smiths London	020 7241 2430
Smiths Birmingham	0121 728 4940	Smiths Manchester	0161 794 8650
Smiths Bristol	0117 971 2800	Smiths Norwich	01603 789 878
Smiths Chelmsford	01245 466 664	Smiths Nottingham	0115 925 4801
Smiths Gateshead	0191 469 5428	Smiths Redruth	01209 315 512
Smiths Horsham	01403 261 981	Smiths Verwood	01202 824 347

Quality & Testing:



0845 527 3331

www.smithmetal.com



info@smithmetal.com