

AMS 6346 (4130)

Technical Datasheet



Service. Quality. Value.

Chromium-Molybdenum Alloy Steel Bar

Typical Applications

Intended for use in the manufacture of parts and components with sections ½" thick or less at time of heat treatments which required a through-hardening steel capable of developing hardness as high as Rockwell "C" 35, and also for parts with greater thickness requiring proportionately lower hardness. It may be used for parts requiring fusion welding. Hardenability and weldability are considered equivalent to 8630 (MIL-S-6250).

Product Description

This chromium-molybdenum alloy is one of the most widely used aircraft steels because of its combination of weldability, ease of fabrication and mild hardenability. In relatively thin sections it will respond to heat treatment to high strength levels and yet in the normalised condition it has adequate strength for many applications. When resistance to wear and abrasion is required, it may be nitrided.

This grade is a quality product melted under the best steelmaking practices for aircraft quality steels. It is vacuum degassed to meet the magnetic particle inspection standards of AMS 2301. The density of this material is typically 7.85kg/dm³.

Machinability

70% for annealed and cold drawn condition. Based on 100% for AISI 1212 steel.

Corrosion Resistance

Low resistance to corrosion.

Weldability

Good.

Production Tolerances

Manufacturing limits are as stated in the Table AMS 2251. For further assistance please contact our Sales Dept / Laboratory.

Related Specifications

- SAE 4130
- UNS G41300
- AMS 6348 (Normalised condition)

Cut to Size Sawn blanks

Cut to Length + 1.0mm - NIL

Chemical Composition (weight %)

	C	Mn	Si	P	S	Cr	Ni	Mo	Cu
Min	0.28	0.40	0.15			0.80		0.15	
Max	0.33	0.60	0.35	0.025	0.025	1.10	0.25	0.25	0.35

Mechanical Properties (minima Heat-Treated Condition)

Tensile Strength (MPa)	862
0.2% Proof Strength (MPa)	689
Elongation on 4D G.L. (%)	17

Bars under 12.70mm hardened and tempered and cold finished.
Bars over 12.70mm hot finished and hardened and tempered or if specified hardened and tempered and cold finished.

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

