

Case Hardening Steel

Product Description

S156 in the British Standard Aerospace Series is a 4% Ni-Cr-Mo case-hardening steel with a tensile strength of 1,320-1,520 MPa. The material is manufactured by consumable electrode vacuum arc re-melting (VAR). Bars, and where practicable, forgings, are subjected to ultrasonic examination. Bars and forgings are supplied in the normalised and softened condition. Parts produced from bar and forgings are required to be supplied in the finally heat treated condition which consists of carburising, hardening and tempering.

Typical Applications

- Aircraft engineering components
- High performance components for autosport

Material Specifications

- BS S156:1976
- BS S82 (related spec. - single melted not VAR)
- 16NCD17 (related French spec. in AIR 9160)
- Wr.N 1.6722/3 (related German spec.)

Availability

- Black bar (S156B)
- Bright bar (S156D)
- Forgings (S156C)
- We stock S156D round bar up to 7 in. (177.8mm) diameter

Chemical Composition (weight %)

Weight (%)	C	Si	Mn	P	S	Cr	Mo	Ni			
Min	0.14	0.10	0.25			1.0	0.20	3.8			
Max	0.18	0.35	0.55	0.015	0.012	1.4	0.30	4.3			

Mechanical Properties

	Minimum	Maximum
UTS, MPa	1,320	1,520
0.2% PS, MPa	1,030	
Elongation, %	11	
Reduction of area, %	40	
Izod impact, ft lbf	30	
Hardness, HBN (normalised + softened)		277

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604 604	Birmingham 01889 576 117	Bristol 0117 971 2800	Chelmsford 01245 466 664	Gateshead 0191 469 5428	Horsham 01403 261 981	Leeds 0113 307 5167
London 020 7241 2430	Manchester 0161 794 8650	Nottingham 0115 925 4801	Norwich 01603 789 878	Redruth 01209 315 512	Verwood 01202 824 347	General 0845 527 3331



ISO 9001



AS 9100



AS 9120



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2017