

Maraging Steel

Typical Applications

- Missile casings
- Tooling
- Ordnance mounting blocks
- High performance motorsport components
- Couplings
- Jet engine and helicopter drive shafts
- Load cells
- Landing gear

Product Description

C200 - a maraging alloy steel containing 8.5% cobalt and 3.3% molybdenum. This steel is produced by vacuum arc re-melting to provide high strength although this is still low when compared with other maraging steels, nominally 200 ksi tensile (1380 MPa) with an above average level of toughness. The alloy retains its strength up to 450°C and good notch impact is maintained down to minus 50°C and below. This material may be nitrided. C200 is usually supplied in the annealed condition where the microstructure consists of fine martensite before final heat treatment.

Machining & Welding

Maraging steels are usually machined in the annealed condition, however, they can be machined in the maraged condition. Components can be machined close to finished dimensions as the low temperature maraging treatment results in minimal distortion. In addition, the small contraction of approximately 0.05% due to maraging results in good dimensional stability.

C200 steel has good weldability.

Availability

Bar and forgings.

Related Specifications

- UNS K29810

Chemical Composition (weight %)

	Ni	Co	Mo	Ti	Al	Si	Mn	C	S	P	Zr	B
Min	18.50	8.50	3.25	0.20	0.10							
Max						0.10	0.10	0.03	0.01	0.01	0.01	0.003

Mechanical Properties (after heat treatment)

Ultimate Tensile Strength	210,000	psi
0.2% Yield Strength	206,000	psi
Elongation	12	%
Reduction of Area	62	%
Notch Tensile (K=9.0)	325,000	psi

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

