

410 Stainless

Technical Datasheet



Service. Quality. Value.

Martensitic Stainless Steel Alloy

Typical Applications

- Gas turbines
- Steam turbines
- Petroleum fractioning structures
- Valves & pumps
- Kitchen utensils
- Fasteners

Product Description

Type 410 stainless is a martensitic alloy commonly supplied in the hardened but still machinable condition. The alloy contains 11.5% chromium which provides good resistance to atmospheric corrosion. However, corrosion resistance is limited unless the alloy is further enhanced by processes including hardening, tempering and polishing. Type 410 displays excellent hardness after heat treatment and the material can be used in the fabrication of highly stressed parts. Weldability of the alloy is generally poor.

Key features

- A commonly used martensitic stainless steel.
- Excellent hardness properties after heat treatment.
- Suitable for highly stressed parts.
- Limited corrosion resistance and weldability is poor.

Machinability

Good but difficult if alloy is hardened above 30HRC.

Weldability

Poor.

Availability

Round bar, plate and sheet

Corrosion resistance

Good resistance to atmospheric corrosion.

Chemical Composition (weight %)

	C	Mn	Si	P	S	Cr	Ni		
min						11.50			
max	0.15	1.00	1.00	0.04	0.03	13.50	0.75		

Mechanical Properties

Tensile strength	700 - 850	MPa
Yield Strength	495	N/mm ²
Elongation A5	15	%

Physical Properties

Density	7800	kg/m ³
Melting Point	1400	°C
Modulus of Elasticity	200	GPa
Electrical Resistivity	570	n Ω.m
Thermal Conductivity at 100°C	24.9	W/m.K

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

