

# AMS 5629 (13/8 PH VAR)

## Technical Datasheet



Service. Quality. Value.

### Precipitation Hardening Stainless Steel Bar

#### Typical Applications

AMS 5629 is ideal for applications where very high strength and toughness are required. This alloy is also used when good general / stress corrosion cracking resistance and minimal property directionality are needed. Applications include aircraft structural parts, landing gear components, shafts, valves, fittings and fasteners. Also used for components in the petrochemical industry.

#### Product Description

13/8 PH VAR is in a family of martensitic precipitation hardening stainless steel along with 17/4 PH and 15/5 PH. It is produced as a consumable electrode, vacuum arc re-melted product offering excellent transverse toughness and ductility even in large section. High strength is developed by a simple low-temperature heat treatment. The various 'H' conditions in the table below indicate the property combination achieved by heat treatment at the temperature shown in degrees F. Due to the chemical composition and controlled melting practice, 13/8 VAR has an essentially ferrite-free microstructure. This material has a typical density of 7.8kg/dm<sup>3</sup>.

#### Machinability

Average cutting speed 80ft/min. 35-40% average (based on 100% for AISI 1212 steel). Alloy is similar to 17/4 PH.

#### Corrosion Resistance

Superior to straight chromium grades like 410, approaching corrosion resistance of the chromium nickel grades. In many corrosive media it is equal to such grades as 302. Corrosion resisting properties will be affected by surface finish and aging heat treatment.

#### Weldability

Excellent and is readily weldable by all commercial processes.

#### Production Tolerances

Manufacturing limits are as stated in the Table AMS 2241. For further assistance please contact our Sales Dept. / Laboratory.

#### Related Specifications

• ASTM SA-564 • UNS S13800

#### Chemical Composition (weight %)

Weight (%)	C	Mn	P	S	Si	Cr	Ni	Mo	Al	N
Min						12.25	7.5	2.00	0.90	
Max	0.05	0.10	0.010	0.008	0.10	13.25	8.5	2.50	1.35	0.01

#### Minimum Mechanical Properties

Condition	Tensile Strength (MPa)	0.2% Proof Stress(MPa)	Elongation on 4D G.L. (%)	Hardness (HB)
H950	1,517	1,413	10	45
H1000	1,413	1,310	10	43
H1025	1,276	1,207	11	41
H1050	1,207	1,138	12	40
H1100	1,034	931	14	34
H1150	931	621	14	30

#### Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

[www.smithmetal.com](http://www.smithmetal.com)

[sales@smithmetal.com](mailto:sales@smithmetal.com)

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

