

#### Typical Applications

- Tooling in the Aerospace Industry
- CNC components
- Mould & gauge making
- General tooling
- Bulkheads
- Retaining rings
- Springs

#### Key features

- Excellent fatigue properties
- Good formability
- High strength & hardness
- Minimum distortion upon heat treatment.
- Good corrosion resistance

#### Availability

Bar

#### Product Description

17-7 PH is a precipitation-hardening stainless steel which combines high strength and hardness. The alloy has excellent fatigue properties, good corrosion resistance and is easily formed. Due to the alloys good mechanical and physical properties, 17-7PH is particularly popular in the aerospace sector and can be used in the manufacture of flat springs up to 315°C (600°F).

#### Corrosion resistance

Good

#### Formability

Good but work hardens rapidly and may require intermediate annealing in deep drawing or in forming intricate parts

#### Chemical Composition (weight %)

	C	Mn	P	S	Si	Cr	Ni	Al		
min						16.00	6.50	0.75		
max	0.09	1.00	0.04	0.03	1.00	18.00	7.75	1.50		

#### Mechanical Properties \*

	A	TH1050	Condition RH 950	C	CH900
UTS, ksi (MPa)	130 (896)	200 (1379)	235 (1620)	220 (1517)	265 (1827)
0.2% YS, ksi (MPa)	40 (276)	185 (1276)	220 (1517)	190 (1310)	260 (1793)
Elongation, % in 2" (50.8 mm)	35	9	6	5	2
Hardness, Rockwell	B85	C43	C48	C43	C49

\* Properties at typical room temperature

#### Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

[www.smithmetal.com](http://www.smithmetal.com)

[sales@smithmetal.com](mailto:sales@smithmetal.com)

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

