

Aerospace Stainless Steel Tube

Typical Applications

- Superheater tubes
- Cooling tubes
- Furnace tubing
- Oil & gas sector applications
- Aerospace applications

Product Description

A type 347, niobium stabilised, stainless steel containing 18% chromium and 10% nickel with added copper. Designed for use in hydraulic applications. Achieves a tensile strength (Rm) of 550/700 N/mm². The alloy benefits from good corrosion resistance and good weldability.

Heat treatment

Supplied in the heat treated condition.

Key features:

- Designed for hydraulic applications
- Niobium stabilised
- Good corrosion resistance
- Good weldability

Corrosion Resistance

Good.

Weldability

Good.

Availability

Tube.

Chemical Composition (weight %)

	C	Cu	Si	Mn	Cr	Ni	Nb	P	S
Min			0.20	0.50	17.0	9.0	5 XC		
Max	0.08	0.50	0.10	2.00	19.0	12.0	1.0	0.035	0.025

Mechanical Properties

Grade	T72 Tube		
Treatment	Solution annealed		
Tensile Strength	550 - 700	Rm, N/mm ²	
Proof Stress	210 - 340	Rp 0.2, N/mm ²	
Elongation in 5.65 √Cross Sectional Area Ruling Section	40	%	
	1/8" OD to 3 1/4 OD		

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

www.smithmetal.com

sales@smithmetal.com

Biggleswade 01767 604604	Birmingham 0121 7284940	Bristol 0117 9712800	Chelmsford 01245 466664	Gateshead 0191 4695428	Horsham 01403 261981	Leeds 0113 3075167
London 020 72412430	Manchester 0161 7948650	Nottingham 0115 9254801	Norwich 01603 789878	Redruth 01209 315512	Verwood 01202 824347	General 0845 5273331



1930

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2018

