Case Hardening Steel



Product Description

S156 in the British Standard Aerospace Series is a 4% Ni-Cr-Mo case-hardening steel with a tensile strength of 1,320-1,520 MPa. The material is manufactured by consumable electrode vacuum arc re-melting (VAR). Bars, and where practicable, forgings, are subjected to ultrasonic examination. Bars and forgings are supplied in the normalised and softened condition. Parts produced from bar and forgings are required to be supplied in the finally heat treated condition which consists of carburising, hardening and tempering.

Typical Applications

- Aircraft engineering components
- · High performance components for autosport

Material Specifications

- BS S156:1976
- BS S82 (related spec. single melted not VAR)
- 16NCD17 (related French spec. in AIR 9160)
- Wr.N 1.6722/3 (related German spec.)

Availability

- Black bar (S156B)
- Bright bar (S156D)
- Forgings (S156C)
- We stock S156D round bar up to 7 in.(177.8mm) diameter

Chemical Composition (weight %)										
Weight (%)	С	Si	Mn	Р	S	Cr	Мо	Ni		
Min	0.14	0.10	0.25			1.0	0.20	3.8		
Max	0.18	0.35	0.55	0.015	0.012	1.4	0.30	4.3		

Mechanical Properties							
	Minimum	Maximum					
UTS, MPa	1,320	1,520					
0.2% PS, MPa	1,030						
Elongation, %	11						
Reduction of area, %	40						
lzod impact, ft lbf	30						
Hardness, HBN (normalised + softened)		277					

Technical Assistance

Our knowledgeable staff backed up by our resident team of qualified metallurgists and engineers, will be pleased to assist further on any technical topic.

UK Service Centres:		Quality & Testing:
Smiths Belfast 02895 908 897 Smiths Biggleswade 01767 604 704 Smiths Birmingham 0121 728 4940 Smiths Bristol 0117 971 2800 Smiths Chelmsford 01245 466 664 Smiths Gateshead 0191 469 5428 Smiths Horsham 01403 261 981	Smiths Leeds 0113 307 5167 Smiths Manchester 0161 794 8650 Smiths Norwich 01603 789 878 Smiths Nottingham 0115 925 4801 Smiths Redruth 01209 315 512 Smiths Verwood 01202 824 347 Main Office 0845 527 3331	bsi Uality Maragement Systems CERTIFIED 1930 Www.smithmetal.com

All information in our data sheet is based on approximate testing and is stated to the best of our knowledge and belief. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of trading. © Smiths Metal Centres 2023